

TECHNICAL SPECIFICATION

GYP SUM PLASTER - A100 FINISH COAT



<u>PROPERTIES</u>	<u>Value</u>
Purity	96.0% min.
Moisture	0.3% w/w max.
Practical Water : Powder Ratio	50 - 60 : 100% w/w
Mixing time @ 300 rpm.	0.5 - 2.0 minutes
Working time	150 – 240 minutes
Color	White / Off-White
Residue on 100 mesh sieve	0.5 % (max)

USAGE : Wall filler and Wall finish coat

PACKING : 25kg PP Bag

